

1 0 1 - 0 0 5 7 1

Appl. No. **TO BE ASSIGNED**

Amdt. dated January 7, 2005

Preliminary Amendment

AMENDMENTS TO THE CLAIMS:

This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS:

Claim 1 (Currently amended). A flame retardant thermoplastic resin composition comprising:

(A) 45 to 95 parts by weight of a thermoplastic polycarbonate resin;

(B) 1 to 50 parts by weight of a vinyl graft copolymer prepared by graft-polymerizing (B-1) 5 to 95 parts by weight of a monomer mixture ~~consisting of~~ comprised of (B-1.1) 50 to 95 by weight of at least one ~~selected from the group consisting~~ of styrene, α -methylstyrene, halogen- or alkyl-substituted styrene, C_{1-8} methacrylic acid alkyl ester, ~~and or~~ or C_{1-8} acrylic acid alkyl ester and (B-1.2) 5 to 50 parts by weight of at least one ~~selected from the group consisting~~ of acrylonitrile, methacrylonitrile, C_{1-8} methacrylic acid alkyl ester, C_{1-8} acrylic acid alkyl ester, maleic acid anhydride, ~~and or~~ or C_{1-4} alkyl- or phenyl N-substituted maleimide onto (B-2) 5 to 95 parts by weight of a rubber polymer selected from the group consisting of butadiene rubber, acryl rubber, ethylene-propylene rubber, styrene-butadiene rubber, acrylonitrile-butadiene rubber, isoprene rubber, copolymer of ethylene-propylene-diene (EPDM), polyorganosiloxane-polyalkyl (meth)acrylate rubber complex and a mixture thereof;

(C) 0 to 50 parts by weight of a vinyl copolymer or a mixture of vinyl copolymer prepared from (C-1) 50 to 95 parts by weight of at least one ~~selected from the group consisting~~ of styrene, α -methyl styrene, halogen or alkyl substituted styrene, C_{1-8} methacrylic acid alkyl ester ~~and or~~ or C_{1-8} acrylic acid alkyl ester and (C-2) 5 to 50 parts by weight of at least one ~~selected from the group consisting~~ of acrylonitrile, methacrylonitrile, C_{1-8}


Appl. No. **TO BE ASSIGNED**

Amdt. dated January 7, 2005


Preliminary Amendment

methacrylic acid alkyl ester, C₁₋₈ acrylic acid alkyl ester, maleic acid anhydride, ~~and~~ or C₁₋₄ alkyl or phenyl N-substituted maleimide;

(D) 1 to 30 parts by weight of a mixture of organic phosphorous compounds ~~consisting of~~ comprising (D-1) 5 to 95 parts by weight of a monomeric phosphoric acid ester compound represented by the following Formula (I) or a mixture thereof and (D-2) 95 to 5 parts by weight of an oligomeric phosphoric acid ester compound represented by the following Formula (II) or a mixture thereof, per 100 parts by weight of the sum of (A), (B) and (C):



wherein R₁ and R₂ are independently hydrogen or a C₁₋₅ alkyl group and x is 0 or an integer from 1 to 3,



wherein R₃, R₄, R₅ and R₆ are independently a C₆₋₂₀ aryl group or an alkyl-substituted C₆₋₂₀ aryl group, respectively, and n is an integer representing the number of repeating units from 1 to 5, the average value of n in the mixture of oligomeric phosphoric acid ester is 1 to 3; and

(E) 0.05 to 5.0 parts by weight of a fluorinated polyolefin resin with average particle size of 0.05 to 1,000 μm and density of 1.2 to 2.3 g/cm³, per 100 parts by weight of (A)+(B)+(C).

Appl. No. **TO BE ASSIGNED**

Amdt. dated January 7, 2005

Preliminary Amendment

Claim 2 (Original). The flame retardant thermoplastic resin composition as defined in claim 1, wherein said R_1 and R_2 are independently hydrogen or alkyl group in which alkyl is methyl, ethyl, isopropyl or t-butyl.

Claim 3 (Currently amended). The flame retardant thermoplastic resin composition as defined in claim 1, wherein said R_3 , R_4 , R_5 and R_6 are independently phenyl group, naphthalene group, ~~and~~ or alkyl-substituted phenyl group in which alkyl is methyl, ethyl, isopropyl and t-butyl.

Claim 4 (Original). A molding article produced from the flame retardant thermoplastic resin composition as defined in claim 1.